


Product	: GRP /FRP Corrugated Sheet
Product Description	: FIBRALAM ® MUV
Product Polser	: Fibralam-AGM.KOD.349.177/51.P5.V01-1,7mm-SNC BLUE-MUV/ST-FT
Reinforcement Form	: Panel Roving
Average Thickness	: 1,70 mm
Color	: SNC BLUE
Surface Coating	: MUV (PET Film)

TECHNICAL CHARACTERISTICS

Properties	Unit	Test Method	Value	Tolerance
Average Thickness	mm	Universal	1,70	±10 %
Mass per Unit Area	kg/m²	Universal	2,45	±10 %
Density	g/cm³	ISO 1183	1,34	1,30 - 1,50
Glass Fiber Content (% by Wt.)	%	EN 1172	27	25 - 30
Water Absorption	%	ISO 62	≤ 0,40	-
Coefficient of Thermal Expansion	m/m/°C	DIN 53752	30X10 ⁻⁶	-
Term Service Temperature	°C		-40 + 120	-
Light Transmission	%	ISO 11664	75	70 - 85
Flame Resistance	Class	EN 13501-1	E S3 d0	-
Barcol Hardness	Barcol	EN 59	45	40 - 50
Tensile Strength	N/mm²	ISO EN 527-4	79	60 - 90
Tensile Modulus	N/mm²	ISO EN 527-4	6517	4500 - 7000
Elongation at Break	%	ISO EN 527-4	1,83	1,50 - 2,50
Flexural Strength	N/mm²	ISO EN 14125	123	100 - 140
Flexural Modulus	N/mm²	ISO EN 14125	3360	2500 - 4000
Flexural Strain	%	ISO EN 14125	2,42	1,80 - 3,50

Profile Drawing

AGM 349 P5



Disclaimer: The data provided herein are based on laboratory testing and represent typical values only. They shall not be considered as a specification or guarantee of product performance. No express or implied warranties, including fitness for a particular purpose, are made. Product performance may vary depending on application methods, processing conditions, and environmental factors. The user is solely responsible for verifying the suitability of the product for its intended use. Polser shall not be liable for any damages arising from improper use, incorrect application, or conditions beyond its control. Polser reserves the right to modify technical data without prior notice.