


SIMONA



SIMONA[®] COPLAST-AS
Coextruded PVC foam sheets
for indoor and outdoor applications

GLOBAL THERMOPLASTIC SOLUTIONS

SIMONA® COPLAST-AS – Versatility breeds success

SIMONA® COPLAST-AS are coextruded PVC foam sheets which are designed to deliver a sophisticated, premium-quality appearance. In addition, COPLAST-AS combines good rigidity with UV and weather stability, making it the perfect solution for outdoor applications.



SIMONA® COPLAST-AS consists of high-quality outer skins and a white foam core. By contrast, SIMONA® COPLAST-AS-X comes with a grey foam core.












Versatile use

- Ceiling and wall panels
- Wall dividers
- Outdoor signs
- Facade elements
- Displays
- Exhibition stand design
- and more

Excellent properties

- UV and weather stability
- High dimensional stability
- Antistatic properties
- Excellent printability
- Sound and heat insulating
- Outstanding processability

Processing versatility

	Sawing
	Bolting
	Drilling
	Riveting
	Backing/laminating
	Gluing
	Warm bending
	Cold curving
	Printing
	Spray painting
	Milling

+ Light but sturdy

The foamed interior is extremely light. At the same time, COPLAST-AS/-X sheets offer good dimensional stability – a key advantage in many fields of application.

+ UV and weather stability

The compact outer skins of COPLAST-AS/-X sheets provide excellent impact strength and high rigidity. Owing to its UV resistance, the material is also suitable for outdoor applications.

+ Antistatic properties

Featuring antistatic properties, COPLAST-AS/-X sheets remain dust-free. This makes laminating and printing much more efficient.




Product range SIMONA® COPLAST-AS Sheets

		SIMONA® COPLAST-AS	SIMONA® COPLAST-AS-X
Coextruded Sheets (formats/thicknesses in mm)			
	2,000 x 1,000	8 to 12	
	2,440 x 1,220	8 to 12	
	3,000 x 1,000	8 to 30	
	3,050 x 1,220	8 to 24	6 to 19
	3,050 x 1,500	8 to 24	3 to 19
	Colours (outer skins/core)	white/white	white/grey

Various formats and thicknesses available from stock. Please contact our sales department for further details concerning availability: sales@simona.de.

Other formats, thicknesses and colours available on request.

Other products: COPLAST-COLOR, COPLAST-AR-X (with anti-slip propertie) and COPLAST-AS(-X)-FR (low flammability)



SIMONA® COPLAST-AS

Material specifications

Material specifications

	SIMONA® COPLAST-AS	SIMONA® COPLAST-AS-X
Density, g/cm ³ , DIN EN ISO 1183	0,67	0,67
Yield stress, MPa, DIN EN ISO 527	18	23
Elongation at yield, %, DIN EN ISO 527	3	3
Tensile modulus of elasticity, MPa, DIN EN ISO 527	1,100	1,100
Flexural modulus of elasticity, MPa, DIN EN ISO 178	1,400	1,400
Impact strength, kJ/m ² , DIN EN ISO 179	23	19
Shore hardness D (15 s), DIN EN ISO 868	70	68
Mean coefficient of linear thermal expansion, K ⁻¹ , ISO 11359-2	0,83 x 10 ⁻⁴	0,83 x 10 ⁻⁴
Specific surface resistance, Ohm, DIN IEC 60093	≤10 ¹²	≤10 ¹²
Fire behaviour, DIN 4102	B2 normal flammability (self-assessment without test certificate), B1 low flammability 10 mm on request	B2 normal flammability (self-assessment without test certificate), B1 low flammability 3 – 8 mm on request
Temperature range, °C	0 to +60	0 to +60
Physiologically safe	–	–

SIMONA AG

Teichweg 16
55606 Kirn
Germany
Phone +49 (0) 67 52 14-0
Fax +49 (0) 67 52 14-211
mail@simona.de
www.simona.de

PRODUCTION SITES

Plant I
Teichweg 16
55606 Kirn
Germany

Plant II
Sulzbacher Straße 77
55606 Kirn
Germany

Plant III
Gewerbestraße 1–2
77975 Ringsheim
Germany

SIMONA Plast-Technik s.r.o.
U Autodílen č.p. 23
43603 Litvínov-Chudeřín
Czech Republic

**SIMONA ENGINEERING PLASTICS
(Guangdong) Co. Ltd.**
No. 368 Jinou Road
High & New Technology Industrial
Development Zone
Jiangmen, Guangdong
China 529000

SIMONA AMERICA INC.
101 Power Boulevard
Archbald, PA 18403
USA

Boltaron Inc.
A SIMONA Group Company
One General Street
Newcomerstown, OH 43832
USA

SALES OFFICES

SIMONA S.A.S. FRANCE
Z.I. 1, rue du Plant Loger
95335 Domont Cedex
France
Phone +33 (0) 1 39 35 49 49
Fax +33 (0) 1 39 91 05 58
mail@simona-fr.com
www.simona-fr.com

SIMONA UK LIMITED
Telford Drive
Brookmead Industrial Park
Stafford ST16 3ST
Great Britain
Phone +44 (0) 1785 222444
Fax +44 (0) 1785 222080
mail@simona-uk.com
www.simona-uk.com

SIMONA AG SWITZERLAND
Industriezone
Bäumlimattstrasse 16
4313 Möhlin
Switzerland
Phone +41 (0) 61 855 9070
Fax +41 (0) 61 855 9075
mail@simona-ch.com
www.simona-ch.com

**SIMONA S.r.l. SOCIETÀ
UNIPERSONALE**
Via Volontari del Sangue 54a
20093 Cologno Monzese (MI)
Italy
Phone +39 02 250851
Fax +39 02 2508520
commerciale@simona-it.com
www.simona-it.com

**SIMONA IBERICA
SEMIELABORADOS S.L.**
Doctor Josep Castells, 26–30
Polígono Industrial Fonollar
08830 Sant Boi de Llobregat
Spain
Phone +34 93 635 4103
Fax +34 93 630 8890
mail@simona-es.com
www.simona-es.com

SIMONA Plast-Technik s.r.o.
Paříkova 910/11a
19000 Praha 9 – Vysočany
Czech Republic
Phone +420 236 160 701
Fax +420 476 767 313
mail@simona-cz.com
www.simona-cz.com

SIMONA POLSKA Sp. z o.o.
ul. Wrocławska 36
Wojkowice k / Wrocławia
55-020 Żórawina
Poland
Phone +48 (0) 71 352 80 20
Fax +48 (0) 71 352 81 40
mail@simona-pl.com
www.simona-pl.com

OOO "SIMONA RUS"
Prospekt Andropova, 18, Bl. 6
115432 Moscow
Russian Federation
Phone +7 (499) 683 00 41
Fax +7 (499) 683 00 42
mail@simona-ru.com
www.simona-ru.com

SIMONA FAR EAST LIMITED
Room 501, 5/F
CCT Telecom Building
11 Wo Shing Street
Fo Tan, Hong Kong
China
Phone +852 29 47 01 93
Fax +852 29 47 01 98
sales@simona-hk.com
www.simona-cn.com

**SIMONA ENGINEERING PLASTICS
TRADING (Shanghai) Co. Ltd.**
Room C, 19/F, Block A
Jia Fa Mansion
129 Da Tian Road, Jing An District
Shanghai
China 200041
Phone +86 21 6267 0881
Fax +86 21 6267 0885
shanghai@simona.com.cn
www.simona-cn.com

SIMONA AMERICA INC.
101 Power Boulevard
Archbald, PA 18403
USA
Phone +1 866 501 2992
Fax +1 800 522 4857
mail@simona-america.com
www.simona-america.com

Boltaron Inc.
A SIMONA Group Company
1 General Street
Newcomerstown, OH 43832
USA
Phone +1 800 342 7444
Fax +1 740 498 5448
info@boltaron.com
www.boltaron.com